SILICONE SEALANT LB-2



according to Regulation (EU) 2015/830



ISSUE DATE: 12.07.2017 REVISION DATE: 12.12.2017 SUPERSEDES DATE: 12.07.2017

VERSION: 1.1

1. SECTION 1: Identification of the substance/mixture and of the company/undertaking

1.1. Product identifier

Trade nameSilicone Sealant LB-2 **Product code**Ford Internal Ref.: 140303

SDS Number 147

Product use Professional use

1.2. Relevant identified uses of the substance or mixture and uses advised against

Relevant identified uses Adhesives, binding agents
Uses advised against No additional information available.

1.3. Details of the supplier of the safety data sheet

Supplier Distributor

Ford-Werke GmbH Ford Motor Company Ltd.
Edsel-Ford-Str. 2-14 Parts Distribution Centre
50769 Cologne Royal Oak Way South

Germany NN11 8NT Daventry, Northants

+49 221 90-33333 United Kingdom sdseu@ford.com +44 1327 305 198

1.4. Emergency telephone number

+49 (0) 6132-84463 (GBK GmbH - 24/7)

2. SECTION 2: Hazards identification

2.1. Classification of the substance or mixture

Classification according to Regulation (EC) No. 1272/2008

Health hazards Serious eye damage/eye irritation, H318 Causes serious eye damage.

Category 1

Skin sensitisation, Category 1 H317 May cause an allergic skin reaction.

Carcinogenicity, Category 2 H351 Suspected of causing cancer.

2.2. Label elements

Labelling according to Regulation (EC) No. 1272/2008

Hazard pictograms



Signal word Danger

Contains Silicon compounds; 2-butanone oxime ; 2-Butanone, O,O',O",O"-

silanetetrayltetraoxime

Hazard statements

H317 May cause an allergic skin reaction.
H318 Causes serious eye damage.

H351 Suspected of causing cancer.

Precautionary statements

Prevention

P201 Obtain special instructions before use..

P280 Wear protective gloves, eye protection, face protection.

Response

P305+P351+P338 IF IN EYES: Rinse cautiously with water for several minutes. Remove contact

lenses, if present and easy to do. Continue rinsing.

P308+P313 IF exposed or concerned: Get medical advice/attention..

2.3. Other hazards

This substance/mixture does not meet the PBT criteria of REACH regulation, annex XIII. This substance/mixture does not meet the vPvB criteria of REACH regulation, annex XIII.

3. SECTION 3: Composition/information on ingredients

3.2. Mixtures

Chemical name	CAS- No EC- No Index No RRN	%	Classification according to Regulation (EC) No. 1272/2008	Notes
Silicon compounds	-	1- < 5	Eye Dam. 1, H318 Skin Sens. 1, H317 STOT RE 2, H373	
2-butanone oxime	96-29-7 202-496-6 616-014-00-0 01-2119539477-28- XXXX	1-<3	Flam. Liq. 3, H226 Acute Tox. 4 (Dermal), H312 Eye Dam. 1, H318 Skin Sens. 1, H317 Carc. 2, H351	
2-Butanone, O,O',O",O"- silanetetrayltetraoxime	34206-40-1 251-882-0 01-2119982966-14- XXXX	0.1 - < 1	Flam. Sol. 1, H228 Eye Irrit. 2, H319 Skin Sens. 1, H317 STOT RE 2, H373	

Full text of H-statements: see section 16

4. SECTION 4: First aid measures

4.1. Description of first aid measures

General informationIF exposed or concerned: Get medical advice/attention.

Inhalation:

Remove person to fresh air and keep comfortable for breathing.

Skin contact: Wash skin with plenty of water. Take off contaminated clothing. If skin irritation

or rash occurs: Get medical advice/attention.

Eyes contact Rinse cautiously with water for several minutes. Remove contact lenses, if

present and easy to do. Continue rinsing. Call a physician immediately.

Ingestion Call a poison center or a doctor if you feel unwell.

4.2. Most important symptoms and effects, both acute and delayed

Symptoms/effects after skin contact May cause an allergic skin reaction.

Symptoms/effects after eye contact Serious damage to eyes.

4.3. Indication of any immediate medical attention and special treatment needed

Treat symptomatically.

5. SECTION 5: Firefighting measures

5.1. Extinguishing media

Suitable extinguishing mediaDry powder. Foam. Carbon dioxide.Unsuitable extinguishing mediaNo additional information available.

5.2. Special hazards arising from the substance or mixture

Hazardous combustion productsDuring fire, gases hazardous to health may be formed.

5.3. Advice for firefighters

Protection during firefighting Do not attempt to take action without suitable protective equipment. Self-

contained breathing apparatus. Complete protective clothing.

6. SECTION 6: Accidental release measures

6.1. Personal precautions, protective equipment and emergency procedures

For non-emergency personnel

Emergency procedures Ventilate spillage area. Avoid contact with skin and eyes. Avoid breathing

dust/fume/gas/mist/vapours/spray.

For emergency responders

Protective equipment Do not attempt to take action without suitable protective equipment. For further

information refer to section 8: "Exposure controls/personal protection".

6.2. Environmental precautions Do not allow to enter drains or water courses.

6.3. Methods and material for containment and cleaning up

Methods for cleaning up Large Spills: Stop leak if safe to do so. Absorb remaining liquid with sand or inert

absorbent and remove to safe place. Flush residue with large amounts of water. Small spills: Wipe up with absorbent material (for example cloth). Clean surface

thoroughly to remove residual contamination.

Other information Dispose of materials or solid residues at an authorized site.

6.4. Reference to other sections For further information refer to section 13.

7. SECTION 7: Handling and storage

7.1. Precautions for safe handling

Precautions for safe handling Ensure good ventilation of the work station. Obtain special instructions before

use. Do not handle until all safety precautions have been read and understood. Wear personal protective equipment. Avoid contact with skin and eyes. Avoid

breathing dust/fume/gas/mist/vapours/spray.

Hygiene measuresContaminated work clothing should not be allowed out of the workplace. Wash

contaminated clothing before reuse. Do not eat, drink or smoke when using this

product. Always wash hands after handling the product.

7.2. Conditions for safe storage, including any incompatibilities

Storage conditions Store locked up. Store in a well-ventilated place. Keep cool.

7.3. Specific end use(s) No additional information available.

8. SECTION 8: Exposure controls/personal protection

8.1. Control parameters

Contains no substances with occupational exposure limits.

DNEL: Derived no effect level

No data available

Cama GmbH, source of supply see www.kcl.de) or comparable product. In case of splash 6 (> 480 minutes) 0.4 Glove recommendation: Camatril Velours® 730 (Kächele contact: Nitrile rubber (NBR) Cama GmbH, source of supply see www.kcl.de) or comparable product.	Components		Туре	Route	Value		Form	
Inhalation: 3.33 mg/m² Long-term - local effects	2-butanone oxime (96-29		Worker	Dermal	1.3 mg/kg		Long-term - systemic	effects
Consumer Dermal 1.5 mg/kg bodyweight Acute - systemic effect Long-term - systemic effect Long-term - systemic effect Inhalation: 2 mg/m² Long-term - systemic effect Inhalation: 2 mg/m² Long-term - systemic effect Inhalation: 0.942 m					•	a3	•	
Inhalation: 2.7 mg/m² Long-term - systemic effect 1.78 mg/kg bodyweight/day Long-term - systemic effect Salanetetray/letraoxime (34206-40-1) Consumer Oral 0.067 mg/kg bodyweight/day Long-term - systemic effect Long-term - systemic Long-term - systemic effect Long-term - systemic Long-term - systemic effect Long-term - systemic Lon			Canaumar		•		•	
Dermal 0.78 mg/kg bodyweight/day Long-term - systemic effect			Consumer					
Inhalation: 2 mg/m² Long-term - local effects					-			
2-Butanone, O,O',O",O"- silanetetray/letraoxime (34206-40-1) Consumer Dermal Con67 mg/kg bodyweight/day Cong-term - systemic effect Long-term - systemic effect Rod available Components Type Route Value Form 2-butanone oxime (96-29-7) Not applicable Freshwater STP 177 mg/l 2-Butanone, O,O',O",O"- silanetetray/letraoxime (34206-40-1) Seawater Consumer Consu					_	g bodyweigni/day	•	
Inhalation: 0.942 mg/m² Long-term - systemic effect (34206-40-1) Consumer Oral 0.067 mg/kg bodyweight/day Long-term - systemic effect Dermal D				innalation:	z mg/m²		Long-term - local effe	ecis
Consumer			Worker	Dermal	0.134 mg/	/kg bodyweight/day	Long-term - systemic	effect
PNEC: Predicted no effect concentration No data available Components Type Route Value Form 2-butanone oxime (96-29-7) Not applicable Freshwater STP 177 mg/l 2-butanone, O,O',O',O'' Seawater 0,4206-40-1) Seawater Soil 1157-93 mg/kg dwt Seawater Soil 1157-93 mg/kg food Serondary Poisoning STP 4.825 mg/l Exposure controls Appropriate engineering controls Appropriate engineering controls Appropriate engineering controls Materials for protective clothing Hand protection Hand protection Hand protection Hand protection Hand protection Hand protection Material Permeation The protective equipment (PPE) Eye protection Hand protection Hand protection The protective equipment (PPE) Eye protection Hand protection The protective equipment (PPE) Eye protection Hand protection The protective equipment (PPE) Eye protection Hand protection The protective equipment (PPE) Safety glasses with side shields Nitrile rubber (NBR) 6 (> 480 minutes) 0.4 Glove recommendation: Camatril Velours® 730 (Kächel Cama GmbH, source of supply see www.kcl.de) or comparable product. Unitrile rubber (NBR) 6 (> 480 minutes) 0.4 Glove recommendation: Camatril Velours® 730 (Kächel Cama GmbH, source of supply see www.kcl.de) or comparable product. Unitrile rubber (NBR) 6 (> 480 minutes) 0.4 Glove recommendation: Camatril Velours® 730 (Kächel Cama GmbH, source of supply see www.kcl.de) or comparable product.		aoxime		Inhalation:	0.942 mg/	/m³	Long-term - systemic	effec
Dermal 0.067 mg/kg bodyweight/day Long-term - systemic effect Concentration No data available Components Type Route Value Form 2-butanone oxime (96-29-7) Not applicable Freshwater 0.118 mg/l Intermittent release STP 177 mg/l 2-butanone, O,O',O'',O'''- Not applicable Freshwater 0.017 mg/l Sianetetrayltetraoxime (34206-40-1) Seaweter 0.002 mg/l Seaweter 0.002 mg/l Seawater 0.002 mg/l Seawater Soil 1157-93 mg/kg dwt Seawater Soil 1157-93 mg/kg food Secondary Poisoning STP 4.825 mg/l Exposure controls Appropriate engineering controls Good general ventilation (typically 10 air changes per hour) should be used. Ventilation rates should be matched to conditions. If applicable, use process enclosures, local exhaust ventilation, or other engineering controls to maintain airborne levels below recommended exposure limits. If exposure limits have not been established, maintain airborne levels to an acceptable level Personal protective equipment should be chosen according to the CEN standard and in discussion with the supplier of the protective equipment Individual protection measures, such as personal protective equipment (PPE) Expe protection Safety glasses with side shields Skin protection Hand protection Hand protection Waterial Permeation Thickness (mm) Comments Venical Permeation Thickness (mm) Comments Venical Safety glasses with side shields Skin protection Safety glasses with side shields Skin protection Good general ventilation, or other engineering controls to maintain or only valid for the supplied product and the stated application. Special working conditions, like heat or mechanical strain, which deviate from the test conditions, can reduce the protective effect provided by the recommended glove Material Permeation Thickness (mm) Comments Comments O, 4 Glove recommendation: Camatril Velours® 730 (Kächeli Cama GmbH, source of supply see www.kcl.de) or comparable product. Glove recommendation: Camatril Velours® 730 (Kächeli Cama GmbH, source of supply see www.kcl.de) or comparable product.	(34206-40-1)		Consumer	Oral	0.067 mg/	/kg bodyweight/day	Long-term - systemic	effec
PNEC: Predicted no effect concentration No data available Components Type Route Value Form 2-butanone oxime (96-29-7) Not applicable Freshwater STP 177 mg/l 2-butanone, O,O',O'',O''- silanetetrayitetraoxime (34206-40-1) Seawater (34206-40-1) Seawater Soil 1157-93 mg/kg dwt Seawater Soil 1157-93 mg/kg food STP 4.825 mg/l Exposure controls Appropriate engineering controls Good general ventilation (typically 10 air changes per hour) should be used. Ventilation rates should be matched to conditions. If applicable, use processe enclosures, local exhaust ventilation, or other engineering controls to maintain airborne levels below recommended exposure limits. If exposure limits have not been established, maintain airborne levels to an acceptable level Personal protective equipment (PPE) Eye protection Materials for protective clothing The protective gloves to be used must comply with the specification of EU directive 99/686/EC and the resultant standard EN374. The above given information is based on laboratory test in line with EN374. The recommended glove conditions, like heat or mechanical strain, which deviate from the test conditions, can reduce the protective effect provided by the recommended glove Material Permeation Thickness (mm) Comments Nitrile rubber (NBR) 6 (> 480 minutes) 0.4 Glove recommendation: Camatril Velours® 730 (Kächeli Cama CmbH, source of supply see www.kcl.de) or comparable product. In case of splash contact: Nitrile rubber (NBR) 6 (> 480 minutes) 0.4 Glove recommendation: Camatril Velours® 730 (Kächeli Cama CmbH, source of supply see www.kcl.de) or comparable product.				Inhalation:	0.232 mg/	m³	Long-term - systemic	effec
Components Type Route Value Form				Dermal	0.067 mg/	/kg bodyweight/day	Long-term - systemic	effect
Components Type Route Value Form			concentration					
2-Butanone, O,O',O'',O'''- silanetetraytletraoxime (34206-40-1) Seawater 0.002 mg/l sediment 9835.346 mg/kg dwt Freshwater Soil 1157.93 mg/kg dwt Seawater Soil 1157.93 mg/kg dwt Oral 2.97 mg/kg food Secondary Poisoning STP 4.825 mg/l Exposure controls Appropriate engineering controls Cood general ventilation (typically 10 air changes per hour) should be used. Ventilation rates should be matched to conditions. If applicable, use process enclosures, local exhaust ventilation, or other engineering controls to maintain airborne levels below recommended exposure limits. If exposure limits have not been established, maintain airborne levels to an acceptable level Personal protective equipment should be chosen according to the CEN standard and in discussion with the supplier of the protective equipment Individual protection measures, such as personal protective equipment (PPE) Eye protection Safety glasses with side shields Skin protection Hand protection Hand protection The protective gloves to be used must comply with the specification of EU directive 89/868/EC and the resultant standard En374. The above given information is based on laboratory test in line with EN374. The ecommendation is only valid for the supplied product and the stated application. Special working conditions, ike heat or mechanical strain, which deviate from the test conditions, can reduce the protective effect provided by the recommended glove Material Permeation Nitrile rubber (NBR) 6 (> 480 minutes) 0.4 Glove recommendation: Camatril Velours® 730 (Kächeli Cama GmbH, source of supply see www.kcl.de) or comparable product. In case of splash 6 (> 480 minutes) 0.4 Glove recommendation: Camatril Velours® 730 (Kächeli Cama GmbH, source of supply see www.kcl.de) or comparable product.		е	Туре	Route	Value		Form	
2-Butanone, O,O',O'',O'''- silanetetraytletraoxime (34206-40-1) Seawater 0.002 mg/l sediment 9835.346 mg/kg dwt Freshwater Soil 1157.93 mg/kg dwt Seawater Soil 1157.93 mg/kg dwt Oral 2.97 mg/kg food Secondary Poisoning STP 4.825 mg/l Exposure controls Appropriate engineering controls Cood general ventilation (typically 10 air changes per hour) should be used. Ventilation rates should be matched to conditions. If applicable, use process enclosures, local exhaust ventilation, or other engineering controls to maintain airborne levels below recommended exposure limits. If exposure limits have not been established, maintain airborne levels to an acceptable level Personal protective equipment should be chosen according to the CEN standard and in discussion with the supplier of the protective equipment Individual protection measures, such as personal protective equipment (PPE) Eye protection Safety glasses with side shields Skin protection Hand protection Hand protection The protective gloves to be used must comply with the specification of EU directive 89/868/EC and the resultant standard En374. The above given information is based on laboratory test in line with EN374. The ecommendation is only valid for the supplied product and the stated application. Special working conditions, ike heat or mechanical strain, which deviate from the test conditions, can reduce the protective effect provided by the recommended glove Material Permeation Nitrile rubber (NBR) 6 (> 480 minutes) 0.4 Glove recommendation: Camatril Velours® 730 (Kächeli Cama GmbH, source of supply see www.kcl.de) or comparable product. In case of splash 6 (> 480 minutes) 0.4 Glove recommendation: Camatril Velours® 730 (Kächeli Cama GmbH, source of supply see www.kcl.de) or comparable product.								
2-Butanone, O,O',O'',O'''- silanetetrayltetraoxime (34206-40-1) Seawater 0.002 mg/l sediment 983.5346 mg/kg dwt Freshwater sediment 983.535 mg/kg dwt Seawater Soil 1157.93 mg/kg dwt Seawater Soil 1157.93 mg/kg dwt Oral 2.97 mg/kg food Secondary Poisoning STP 4.825 mg/l Exposure controls Appropriate engineering controls Appropriate engineering controls Good general ventilation (typically 10 air changes per hour) should be used. Ventilation rates should be matched to conditions. If applicable, use process enclosures, local exhaust ventilation, or other engineering controls to maintain airborne levels below recommended exposure limits. If exposure limits have not been established, maintain airborne levels to an acceptable level Personal protective equipment should be chosen according to the CEN standard and in discussion with the supplier of the protective equipment Individual protection measures, such as personal protective equipment (PPE) Eye protection Skin protection Hand protection Hand protection The protective gloves to be used must comply with the specification of EU directive 89/686/EC and the resultant standard EN374. The above given information is based on laboratory test in line with EN374. The above given information is based on laboratory test in line with EN374. The above given information is based on laboratory test in line with EN374. The ecommendation is only valid for the supplied product and the stated application. Special working conditions, can reduce the protective effect provided by the recommended glove Material Permeation Nitrile rubber (NBR) 6 (> 480 minutes) 0.4 Glove recommendation: Camatril Velours® 730 (Kächeli Cama GmbH, source of supply see www.kcl.de) or comparable product. In case of splash contact. Nitrile rubber (NBR) 6 (> 480 minutes) 0.4 Glove recommendation: Camatril Velours® 730 (Kächeli Cama GmbH, source of supply see www.kcl.de) or comparable product.	2-butanone oxin	ne (96-29-7)	Not applicable		_			
2-Butanone, O,O',O",O"- silanetetrayltetraoxime (34206-40-1) Seawater 0.002 mg/l sediment 9833-346 mg/kg dwt Freshwater sediment 9833-346 mg/kg dwt Seawater Soil 1157-93 mg/kg dwt Oral 2.97 mg/kg food Secondary Poisoning STP 4.825 mg/l Exposure controls Appropriate engineering controls Good general ventilation (typically 10 air changes per hour) should be used. Ventilation rates should be matched to conditions. If applicable, use process enclosures, local exhaust ventilation, or other engineering controls to maintain airborne levels below recommended exposure limits. If exposure limits have not been established, maintain airborne levels to an acceptable level Personal protective equipment should be chosen according to the CEN standard and in discussion with the supplier of the protective equipment Individual protection Individual protection Waterial The protective equipment (PPE) Safety glasses with side shields Skin protection Hand protection The protective gloves to be used must comply with the specification of EU directive 89/666/EC and the resultant standard EN374. The above given information is based on laboratory test in line with EN374. The above given information is based on laboratory test in line with EN374. The recommendation is only valid for the supplied product and the stated application. Special working conditions, like heat or mechanical strain, which deviate from the test conditions, can reduce the protective effect provided by the recommended glove Material Permeation Thickness (mm) Comments Nitrile rubber (NBR) 6 (> 480 minutes) 0.4 Glove recommendation: Camatril Velours® 730 (Kächeli Cama GmbH, source of supply see www.kcl.de) or comparable product. Glove recommendation: Camatril Velours® 730 (Kächeli Cama GmbH, source of supply see www.kcl.de) or comparable product.					•	/I	Intermittent release	
Seawater 0.002 mg/l sediment 9835.346 mg/kg dwt Freshwater sediment 9835.346 mg/kg dwt Seawater Soil 1157.93 mg/kg dwt Oral 2.97 mg/kg food Secondary Poisoning STP 4.825 mg/l Exposure controls Appropriate engineering controls Good general ventilation (typically 10 air changes per hour) should be used. Ventilation rates should be matched to conditions. If applicable, use process enclosures, local exhaust ventilation, or other engineering controls to maintain airborne levels below recommended exposure limits. If exposure limits have not been established, maintain airborne levels to an acceptable level Personal protective equipment should be chosen according to the CEN standard and in discussion with the supplier of the protective equipment Individual protection measures, such as personal protective equipment (PPE) Eye protection Hand protection Hand protection The protective gloves to be used must comply with the specification of EU directive 89/686/EC and the resultant standard EN374. The above given information is based on laboratory test in line with EN374. The above given information is based on laboratory test in line with EN374. The accommendation is only valid for the supplied product and the stated application. Special working conditions, like heat or mechanical strain, which deviate from the test conditions, can reduce the protective effect provided by the recommended glove Material Permeation Thickness (mm) Comments Nitrile rubber (NBR) 6 (> 480 minutes) 0.4 Glove recommendation: Camatril Velours® 730 (Kächeli Cama GmbH, source of supply see www.kcl.de) or comparable product. Cama GmbH, source of supply see www.kcl.de) or comparable product.				STP	177 mg/l			
Seawater 0.002 mg/l sediment 9835.346 mg/kg dwt Freshwater sediment 9835.346 mg/kg dwt Seawater Soil 1157.93 mg/kg dwt Seawater Soil 1157.93 mg/kg dwt Oral 2.97 mg/kg food Secondary Poisoning STP 4.825 mg/l Exposure controls	2-Butanone, O,0	O',O",O"'-	Not applicable	Freshwater	0.017 mg/	/1		
sediment 9835.346 mg/kg dwt Freshwater sediment 983.535 mg/kg dwt Seawater Soil 1157.93 mg/kg dwt Seawater Soil 1157.93 mg/kg dwt Seawater Soil 1157.93 mg/kg dwt Secondary Poisoning STP 4.825 mg/l Exposure controls Appropriate engineering controls Good general ventilation (typically 10 air changes per hour) should be used. Ventilation rates should be matched to conditions. If applicable, use process enclosures, local exhaust ventilation, or other engineering controls to maintain airborne levels below recommended exposure limits. If exposure limits have not been established, maintain airborne levels to an acceptable level Personal protective equipment should be chosen according to the CEN standard and in discussion with the supplier of the protective equipment (PPE) Eye protection Individual protection measures, such as personal protective equipment (PPE) Eye protection Safety glasses with side shields Skin protection Hand protection The protective gloves to be used must comply with the specification of EU directive 89/686/EC and the resultant standard EN374. The above given information is based on laboratory test in line with EN374. The recommendation is only valid for the supplied product and the stated application. Special working conditions, like heat or mechanical strain, which deviate from the test conditions, can reduce the protective effect provided by the recommended glove Material Permeation Nitrile rubber (NBR) 6 (> 480 minutes) 0.4 Glove recommendation: Camatril Velours® 730 (Kächeli Cama GmbH, source of supply see www.kcl.de) or comparable product. In case of splash 6 (> 480 minutes) 0.4 Glove recommendation: Camatril Velours® 730 (Kächeli Cama GmbH, source of supply see www.kcl.de) or comparable product.		aoxime		Seawater	0.002 mg/	/ I		
Sediment 983.535 mg/kg dwt Seawater	(34206-40-1)			sediment	9835.346	mg/kg dwt	Freshwater	
Soil 1157.93 mg/kg dwt Oral 2.97 mg/kg dod Secondary Poisoning STP 4.825 mg/l				sediment			Seawater	
Coral 2.97 mg/kg food Secondary Poisoning STP 4.825 mg/l				Soil				
Exposure controls Appropriate engineering controls Good general ventilation (typically 10 air changes per hour) should be used. Ventilation rates should be matched to conditions. If applicable, use process enclosures, local exhaust ventilation, or other engineering controls to maintain airborne levels below recommended exposure limits. If exposure limits have not been established, maintain airborne levels to an acceptable level Personal protective equipment should be chosen according to the CEN standard and in discussion with the supplier of the protective equipment [PPE] Eye protection Individual protection measures, such as personal protective equipment (PPE) Eye protection Skin protection Hand protection The protective gloves to be used must comply with the specification of EU directive 89/686/EC and the resultant standard EN374. The above given information is based on laboratory test in line with EN374. The recommendation is only valid for the supplied product and the stated application. Special working conditions, like heat or mechanical strain, which deviate from the test conditions, can reduce the protective effect provided by the recommended glove Material Permeation Nitrile rubber (NBR) 6 (> 480 minutes) 0.4 Glove recommendation: Camatril Velours® 730 (Kächelicama GmbH, source of supply see www.kcl.de) or comparable product. In case of splash 6 (> 480 minutes) 0.4 Glove recommendation: Camatril Velours® 730 (Kächelicantact: Nitrile rubber (NBR)				Oral		0 0	Secondary Poisoning	1
Appropriate engineering controls Good general ventilation (typically 10 air changes per hour) should be used. Ventilation rates should be matched to conditions. If applicable, use process enclosures, local exhaust ventilation, or other engineering controls to maintain airborne levels below recommended exposure limits. If exposure limits have not been established, maintain airborne levels to an acceptable level Personal protective equipment should be chosen according to the CEN standard and in discussion with the supplier of the protective equipment Individual protection measures, such as personal protective equipment (PPE) Eye protection Individual protection measures, such as personal protective equipment (PPE) Eye protection The protective gloves to be used must comply with the specification of EU directive 89/686/EC and the resultant standard EN374. The above given information is based on laboratory test in line with EN374. The recommendation is only valid for the supplied product and the stated application. Special working conditions, like heat or mechanical strain, which deviate from the test conditions, can reduce the protective effect provided by the recommended glove Material Permeation Nitrile rubber (NBR) 6 (> 480 minutes) O.4 Glove recommendation: Camatril Velours® 730 (Kächele Cama GmbH, source of supply see www.kcl.de) or comparable product. In case of splash 6 (> 480 minutes) O.4 Glove recommendation: Camatril Velours® 730 (Kächele Cama GmbH, source of supply see www.kcl.de) or comparable product.				STP	-	-	,	,
Ventilation rates should be matched to conditions. If applicable, use process enclosures, local exhaust ventilation, or other engineering controls to maintain airborne levels below recommended exposure limits. If exposure limits have not been established, maintain airborne levels to an acceptable level Materials for protective clothing Materials for protection measures, such as personal protective equipment should be chosen according to the CEN standard and in discussion with the supplier of the protective equipment Individual protection measures, such as personal protective equipment (PPE) Eye protection Safety glasses with side shields Skin protection The protective gloves to be used must comply with the specification of EU directive 89/686/EC and the resultant standard EN374. The above given information is based on laboratory test in line with EN374. The recommendation is only valid for the supplied product and the stated application. Special working conditions, like heat or mechanical strain, which deviate from the test conditions, can reduce the protective effect provided by the recommended glove Material Permeation Nitrile rubber (NBR) 6 (> 480 minutes) O.4 Glove recommendation: Camatril Velours® 730 (Kächelicandatt: Nitrile rubber (NBR) In case of splash 6 (> 480 minutes) O.4 Glove recommendation: Camatril Velours® 730 (Kächelicandatt: Nitrile rubber (NBR) Cama GmbH, source of supply see www.kcl.de) or comparable product.	Exposure cor	ntrols						
been established, maintain airborne levels to an acceptable level Personal protective equipment should be chosen according to the CEN standard and in discussion with the supplier of the protective equipment Individual protection measures, such as personal protective equipment (PPE) Eye protection Skin protection Hand protection Hand protection The protective gloves to be used must comply with the specification of EU directive 89/686/EC and the resultant standard EN374. The above given information is based on laboratory test in line with EN374. The recommendation is only valid for the supplied product and the stated application. Special working conditions, like heat or mechanical strain, which deviate from the test conditions, can reduce the protective effect provided by the recommended glove Material Permeation Thickness (mm) Comments Nitrile rubber (NBR) 6 (> 480 minutes) 0.4 Glove recommendation: Camatril Velours® 730 (Kächelic Cama GmbH, source of supply see www.kcl.de) or comparable product. In case of splash contact: Nitrile rubber (NBR) O.4 Glove recommendation: Camatril Velours® 730 (Kächelic Cama GmbH, source of supply see www.kcl.de) or comparable product.	Appropriate en	gineering co	ntrols	Ventilation rate	tes should b ocal exhaust	e matched to conditio ventilation, or other e	ns. If applicable, use proces ngineering controls to main	ss tain
Individual protection measures, such as personal protective equipment (PPE) Eye protection Safety glasses with side shields Skin protection Hand protection The protective gloves to be used must comply with the specification of EU directive 89/686/EC and the resultant standard EN374. The above given information is based on laboratory test in line with EN374. The recommendation is only valid for the supplied product and the stated application. Special working conditions, like heat or mechanical strain, which deviate from the test conditions, can reduce the protective effect provided by the recommended glove Material Permeation Thickness (mm) Comments Nitrile rubber (NBR) 6 (> 480 minutes) 0.4 Glove recommendation: Camatril Velours® 730 (Kächele Cama GmbH, source of supply see www.kcl.de) or comparable product. In case of splash contact: Nitrile rubber (NBR) 6 (> 480 minutes) Cama GmbH, source of supply see www.kcl.de) or comparable product.	Materials for pr	otective clot	hing	been establis Personal prot	hed, maintai ective equip	in airborne levels to an ment should be chose	n acceptable level en according to the CEN sta	
Skin protection Hand protection The protective gloves to be used must comply with the specification of EU directive 89/686/EC and the resultant standard EN374. The above given information is based on laboratory test in line with EN374. The recommendation is only valid for the supplied product and the stated application. Special working conditions, like heat or mechanical strain, which deviate from the test conditions, can reduce the protective effect provided by the recommended glove Material Permeation Thickness (mm) Comments O.4 Glove recommendation: Camatril Velours® 730 (Kächele Cama GmbH, source of supply see www.kcl.de) or comparable product. In case of splash Cama GmbH, source of supply see www.kcl.de) or comparable product. Glove recommendation: Camatril Velours® 730 (Kächele Cama GmbH, source of supply see www.kcl.de) or comparable product.	Individual prote	ection meası	ires, such as pe					
Hand protection The protective gloves to be used must comply with the specification of EU directive 89/686/EC and the resultant standard EN374. The above given information is based on laboratory test in line with EN374. The recommendation is only valid for the supplied product and the stated application. Special working conditions, like heat or mechanical strain, which deviate from the test conditions, can reduce the protective effect provided by the recommended glove Material Permeation Thickness (mm) Comments O.4 Glove recommendation: Camatril Velours® 730 (Kächelicama GmbH, source of supply see www.kcl.de) or comparable product. In case of splash Cama GmbH, source of supply see www.kcl.de) or comparable product. Glove recommendation: Camatril Velours® 730 (Kächelicama GmbH, source of supply see www.kcl.de) or comparable product.	• •			Safety glasse	s with side s	shields		
directive 89/686/EC and the resultant standard EN374. The above given information is based on laboratory test in line with EN374. The recommendation is only valid for the supplied product and the stated application. Special working conditions, like heat or mechanical strain, which deviate from the test conditions, can reduce the protective effect provided by the recommended glove Material Permeation Comments	•							
Material Permeation Thickness (mm) Comments Nitrile rubber (NBR) 6 (> 480 minutes) 0.4 Glove recommendation: Camatril Velours® 730 (Kächele Cama GmbH, source of supply see www.kcl.de) or comparable product. In case of splash contact: Nitrile rubber (NBR) 6 (> 480 minutes) 0.4 Glove recommendation: Camatril Velours® 730 (Kächele Cama GmbH, source of supply see www.kcl.de) or comparable product.	Hand prote	ction		directive 89/6 information is is only valid for conditions, like	86/EC and to based on late the supplication or the supplication makes the supplication of the supplication	he resultant standard aboratory test in line we ed product and the sta echanical strain, which	EN374. The above given ith EN374. The recommend ated application. Special wo a deviate from the test cond	rking
Cama GmbH, source of supply see www.kcl.de) or comparable product. In case of splash 6 (> 480 minutes) 0.4 Glove recommendation: Camatril Velours® 730 (Kächele contact: Nitrile rubber (NBR) Cama GmbH, source of supply see www.kcl.de) or comparable product.	Material	Perm	eation		•	•	Ü	
In case of splash 6 (> 480 minutes) 0.4 Glove recommendation: Camatril Velours® 730 (Kächele contact: Nitrile rubber (NBR) Cama GmbH, source of supply see www.kcl.de) or comparable product.	Nitrile rubber (N	BR) 6 (> 4	80 minutes)					
code: Ford Internal Ref : 1/0303	contact: Nitrile rubber			O.4 Glove recommendation: Camatril Velours® 73 Cama GmbH, source of supply see www.kcl.o				
COUG. FOR HILDING INC. 140000 TAR - PIT REMISION MAILS TO TO THE PIT TO THE P	code: Ford Internal Ref	.: 140303		GB - en		Revision	date: 12/12/2017	4/

Other protective measures No additional information available.

Respiratory protection In case of insufficient ventilation, wear suitable respiratory equipment **Thermal hazard protection** Wear appropriate thermal protective clothing, when necessary.

Environmental exposure controlsAvoid release to the environment.

9. SECTION 9: Physical and chemical properties

9.1. Information on basic physical and chemical properties

Physical stateSolidAppearancePaste.ColourBlack.OdourSlight.

Odour threshold No data available No data available No data available Relative evaporation rate (butylacetate=1) **Melting point** Not applicable Freezing point No data available **Boiling point** No data available > 93 °C Closed cup Flash point Auto-ignition temperature No data available **Decomposition temperature** No data available Not applicable Flammability (solid, gas) < 5 mm Hg Vapour pressure Relative vapour density at 20 °C No data available No data available Relative density **Density** 1.31 g/cm³

Solubility Water: Polymerisation can occur

Log PowNo data availableViscosity, kinematicNo data availableViscosity, dynamicNo data availableExplosive propertiesNo data availableOxidising propertiesNo data availableExplosive limitsNo data available

9.2. Other information

VOC (EU) < 5 %

10. SECTION 10: Stability and reactivity

10.1. Reactivity The product is non-reactive under normal conditions of use, storage and

transport.

10.2. Chemical stability Stable under normal conditions.

10.3. Possibility of hazardous reactions No dangerous reactions known under normal conditions of use.

10.4. Conditions to avoid Avoid contact with : Water, humidity.

10.5. Incompatible materials No additional information available.

10.6. Hazardous decomposition products

Methanol decomposes slowly on exposure to water (moisture). Hardening: ethyl methyl ketoxime.

11. SECTION 11: Toxicological information

11.1. Information on toxicological effects

Acute toxicity Based on available data, the classification criteria are not met

Mixture

Name	Method	Type	Exposure route	Value	Unit	Species	Remarks
Silicone Sealant LB-2		ATE	Dermal	> 5000	mg/kg		(calculated value)
Substance							
Name	Method	Туре	Exposure route	Value	Unit	Species	Remarks
2-butanone oxime (96-29-7)		ATE	Dermal	1100	mg/kg		
Skin corrosion/irritatio	n		Based on available	data, the c	lassificatio	n criteria are n	ot met
Serious eye damage/iri	ritation		Causes serious eye	damage.			
Respiratory or skin ser	nsitisation		May cause an allerg	jic skin rea	ction.		
Germ cell mutagenicity	1		Based on available	data, the c	lassificatio	n criteria are n	ot met
Carcinogenicity			Suspected of causir	ng cancer.			
Reproductive toxicity			Based on available	data, the c	lassificatio	n criteria are n	ot met
STOT-single exposure			Based on available	data, the c	lassificatio	n criteria are n	ot met
STOT-repeated exposu	ire		Based on available	data, the c	lassificatio	n criteria are n	ot met

12. SECTION 12: Ecological information

12.1. Toxicity

Ecology - general The product is not considered harmful to aquatic organisms nor to cause long-

term adverse effects in the environment.

Based on available data, the classification criteria are not met

12.2. Persistence and degradability

No additional information available.

12.3. Bioaccumulative potential

Aspiration hazard

No additional information available.

12.4. Mobility in soil

No additional information available.

12.5. Results of PBT and vPvB assessment

Silicone Sealant LB-2

This substance/mixture does not meet the PBT criteria of REACH regulation, annex XIII.

This substance/mixture does not meet the vPvB criteria of REACH regulation, annex XIII.

12.6. Other adverse effects

Other adverse effects No other adverse environmental effects (e.g. ozone depletion, photochemical

ozone creation potential, endocrine disruption, global warming potential) are

expected from this product.

13. **SECTION 13: Disposal considerations**

13.1. Waste treatment methods

Waste treatment methods Dispose of contents/container in accordance with licensed collector's sorting

> instructions. Empty containers or liners may retain some product residues. This material and its container must be disposed of in a safe manner (see: Disposal

instructions).

Product/Packaging disposal

recommendations

Do not discharge into surface water. Empty containers should be taken to an

approved waste handling site for recycling or disposal.

Ecology - waste materials

European List of Waste (LoW) code 08 04 09*

waste adhesives and sealants containing organic solvents or

other dangerous substances

Avoid release to the environment.

15 01 10* packaging containing residues of or contaminated by

dangerous substances

14. **SECTION 14: Transport information**

In accordance with ADR / RID / IMDG / IATA / ADN Not regulated for transport

15. **SECTION 15: Regulatory information**

15.1. Safety, health and environmental regulations/legislation specific for the substance or mixture

EU-Regulations

The following restrictions are applicable according to Annex XVII of the REACH Regulation (EC) No 1907/2006

2-butanone oxime 3. Liquid substances or mixtures which are regarded as dangerous in accordance with Directive 1999/45/EC or are fulfilling the criteria for any of the

following hazard classes or categories set out in Annex I to Regulation (EC) No

1272/2008

2-butanone oxime 3(a) Substances or mixtures fulfilling the criteria for any of the following hazard

classes or categories set out in Annex I to Regulation (EC) No 1272/2008: Hazard classes 2.1 to 2.4, 2.6 and 2.7, 2.8 types A and B, 2.9, 2.10, 2.12, 2.13

categories 1 and 2, 2.14 categories 1 and 2, 2.15 types A to F

3(b) Substances or mixtures fulfilling the criteria for any of the following hazard Silicone Sealant LB-2 - 2-butanone oxime

classes or categories set out in Annex I to Regulation (EC) No 1272/2008: Hazard classes 3.1 to 3.6, 3.7 adverse effects on sexual function and fertility or

on development, 3.8 effects other than narcotic effects, 3.9 and 3.10

Contains no substance on the REACH candidate list

Contains no REACH Annex XIV substances

VOC (EU) < 5 %

Other information, restriction and prohibition regulations

Pregnant/breastfeeding women working with the product must not be in direct contact with the product. Young people below the age of 18 years are not allowed to use the product. Directive 98/24/EC on the protection of the health and safety of workers from the risks related to chemical agents at work, as

amended. For details, refer to section 3 and 8.

National regulations

No additional information available.

15.2. Chemical safety assessment

No chemical safety assessment has been carried out

16. **SECTION 16: Other information**

Indication of changes

SECTION 8.

Abbreviations and acronyms

ADN European Agreement concerning the International Carriage of Dangerous Goods by Inland

Waterways.

ADR European Agreement concerning the International Carriage of Dangerous Goods by Road.

ATE Acute Toxicity Estimate.

BCF Bioconcentration factor.

CAO Cargo Aircraft Only.

CLP Classification Labelling Packaging Regulation; Regulation (EC) No 1272/2008.

DMEL Derived Minimal Effect level.

DNEL Derived-No Effect Level.

EC50 Median effective concentration.

IARC International Agency for Research on Cancer.

IATA International Air Transport Association.

IMDG International Maritime Dangerous Goods.

LC50 Median lethal concentration.

LD50 Median lethal dose.

LOAEL Lowest Observed Adverse Effect Level.

NOAEC No-Observed Adverse Effect Concentration.

NOAEL No-Observed Adverse Effect Level.

NOEC No-Observed Effect Concentration.

OECD Organisation for Economic Co-operation and Development.

PBT Persistent Bioaccumulative Toxic.

PNEC Predicted No-Effect Concentration.

REACH Registration, Evaluation, Authorisation and Restriction of Chemicals Regulation (EC) No

1907/2006

RID Regulations concerning the International Carriage of Dangerous Goods by Rail.

SDS Safety Data Sheet.
STP Sewage treatment plant.
TLM Median Tolerance Limit.

vPvB Very Persistent and Very Bioaccumulative.

SDS Safety Data Sheet.

OEL Occupational Exposure Limit.

RRN REACH Registration no..

PCA Passenger and Cargo Aircraft.

CAO Cargo Aircraft only.

Data sources REGULATION (EC) No 1272/2008 OF THE EUROPEAN PARLIAMENT AND

OF THE COUNCIL of 16 December 2008 on classification, labelling and packaging of substances and mixtures, amending and repealing Directives 67/548/EEC and 1999/45/EC, and amending Regulation (EC) No 1907/2006..

Training advice Normal use of this product shall imply use in accordance with the instructions on

the packaging

Full text of H- and EUH-statements

Acute Tox. 4 (Dermal) Acute toxicity (dermal), Category 4.

Carc. 2 Carcinogenicity, Category 2.

Eye Dam. 1 Serious eye damage/eye irritation, Category 1.
Eye Irrit. 2 Serious eye damage/eye irritation, Category 2.

Flam. Liq. 3 Flammable liquids, Category 3.
Flam. Sol. 1 Flammable solids, Category 1.
Skin Sens. 1 Skin sensitisation, Category 1.

STOT RE 2	Specific target organ toxicity — Repeated exposure, Category 2.
H226	Flammable liquid and vapour.
H228	Flammable solid.
H312	Harmful in contact with skin.
H317	May cause an allergic skin reaction.
H318	Causes serious eye damage.
H319	Causes serious eye irritation.
H351	Suspected of causing cancer.
H373	May cause damage to organs through prolonged or repeated exposure.

Classification and procedure used to derive the classification for mixtures according to Regulation (EC) 1272/2008 [CLP]

= =			
Eye Dam. 1	H318	Calculation method	
Skin Sens. 1	H317	Calculation method	
Carc. 2	H351	Calculation method	

The above information describes exclusively the safety requirements of the product and is based on our present-day knowledge. The information is intended to give you advice about the safe handling of the product named in this safety data sheet, for storage, processing, transport and disposal. The information cannot be transferred to other products. In the case of mixing the product with other products or in the case of processing, the information on this safety data sheet is not necessarily valid for the new made-up material.

9/9

Attachment to the Safety Data Sheet



Product Name:Silicone Sealant LB-2Page:1/1Ford Int. Ref. No.:140303Print Date:12.12.2017

Involved Products:

Finiscode Part number Container Size:

1. 2 190 442 HU7J M4G323 AA 50 ml

Part of Kit:

2 257 899 BK2Q 6A729 AC Transit Oil Pump Warranty Kit